

EPSOM

PRODUCT INFORMATION



Packaging	Shrink wrapped & Palletised
-----------	-----------------------------

TECHNICAL INFORMATION

Brick Dimensions (L x W x H)	215 x 102 x 65mm
Size Tolerances Mean & Range	T2, R1
Configuration	Frogged
Voids	NPD
Mean Compressive Strength	≥25 N/mm ²
Active Soluble Salts	S2
Water Absorption	≤14%
Durability	F2
Gross Dry Density	1800 Kg/m ³
Equivalent Thermal Conductivity	0,21 W/ mK
Initial Rate of Absorption	1.5-4.0 Kg/(m ² ·min)

www.brickability.co.uk

0870 143 3332

Queensgate House, Cookham Road, Bracknell, Berkshire RG12 1RB

Issue Date: December 2023