

## ASCOT

## PRODUCT INFORMATION



[www.brickability.co.uk](http://www.brickability.co.uk)

0870 143 3332

Queensgate House, Cookham Road, Bracknell, Berkshire RG12 1RB

Issue Date: October 2025

|           |                             |
|-----------|-----------------------------|
| Packaging | Shrink wrapped & Palletised |
|-----------|-----------------------------|

## TECHNICAL INFORMATION

|                                 |                                  |
|---------------------------------|----------------------------------|
| Brick Dimensions (L x W x H)    | 215 x 102 x 65mm                 |
| Size Tolerances Mean & Range    | T1, R1                           |
| Configuration                   | Frogged                          |
| Voids                           | NPD                              |
| Mean Compressive Strength       | $\geq 12.5 \text{ N/mm}^2$       |
| Active Soluble Salts            | S2                               |
| Water Absorption                | $\leq 16\%$                      |
| Durability                      | F2                               |
| Gross Dry Density               | 1850 Kg/m <sup>3</sup>           |
| Equivalent Thermal Conductivity | NPD                              |
| Initial Rate of Absorption      | 1.5-4.0 Kg/(m <sup>2</sup> ·min) |