

EPSOM

PRODUCT INFORMATION



www.brickability.co.uk

0870 143 3332

Queensgate House, Cookham Road, Bracknell, Berkshire RG12 1RB

Issue Date: October 2025

Packaging	Shrink wrapped & Palletised
-----------	-----------------------------

TECHNICAL INFORMATION

Brick Dimensions (L x W x H)	215 x 102 x 65mm
Size Tolerances Mean & Range	T1, R1
Configuration	Frogged
Voids	NPD
Mean Compressive Strength	$\geq 25 \text{ N/mm}^2$
Active Soluble Salts	S2
Water Absorption	$\leq 14\%$
Durability	F2
Gross Dry Density	1800 Kg/m^3
Equivalent Thermal Conductivity	$0,21 \text{ W/ mK}$
Initial Rate of Absorption	$1.5\text{-}4.0 \text{ Kg/(m}^2\cdot\text{min)}$