


## KINGSTON

## PRODUCT INFORMATION



Packaging	Shrink wrapped & Palletised
-----------	-----------------------------

## TECHNICAL INFORMATION

Brick Dimensions (L x W x H)	215 x 102 x 65mm
Size Tolerances Mean & Range	T2, R1
Configuration	Frogged
Voids	NPD
Mean Compressive Strength	$\geq 12.5 \text{ N/mm}^2$
Active Soluble Salts	S2
Water Absorption	$\leq 16\%$
Durability	F2
Gross Dry Density	1850 Kg/m <sup>3</sup>
Equivalent Thermal Conductivity	NPD
Initial Rate of Absorption	1.5-4.0 Kg/(m <sup>2</sup> ·min)

[www.brickability.co.uk](http://www.brickability.co.uk)

0870 143 3332

Queensgate House, Cookham Road, Bracknell, Berkshire RG12 1RB

Issue Date: December 2023