

## LANZAROTE BLACK



[www.brickability.co.uk](http://www.brickability.co.uk)

0870 143 3332

Queensgate House, Cookham Road, Bracknell, Berkshire RG12 1RB

Issue Date: July 2022

## PRODUCT INFORMATION

Packaging	Shrink wrapped & Palletised
-----------	-----------------------------

## TECHNICAL INFORMATION

Brick Dimensions (L x W x H)	215 x 102 x 65mm
Size Tolerances Mean & Range	T2, R2
Configuration	Perforated
Voids	≤ 37%
Mean Compressive Strength	40 N/mm <sup>2</sup>
Active Soluble Salts	S2
Water Absorption	≤6%
Durability	F2
Gross Dry Density	1400 Kg/m <sup>3</sup>
Equivalent Thermal Conductivity	0,21 W/ mK
Initial Rate of Absorption	0,8 Kg/(m <sup>2</sup> ·min)