

MALVERN VILLAGE MIXTURE



www.brickability.co.uk

0870 143 3332

Queensgate House, Cookham Road, Bracknell, Berkshire RG12 1RB

Issue Date: May 2022

PRODUCT INFORMATION

| | |
|-----------|----------------|
| Packaging | Shrink wrapped |
|-----------|----------------|

TECHNICAL INFORMATION

| | |
|---------------------------------|------------------------------|
| Brick Dimensions (L x W x H) | 215 x 102 x 65mm |
| Size Tolerances Mean & Range | T2, R1 |
| Configuration | Frogged |
| Voids | ≤18% |
| Mean Compressive Strength | ≥25 N/mm ² |
| Active Soluble Salts | S2 |
| Water Absorption | 13% |
| Durability | F2 |
| Gross Dry Density | NPD Kg/m ³ |
| Equivalent Thermal Conductivity | NPD W/ mK |
| Initial Rate of Absorption | NPD Kg/(m ² ·min) |