

## SEVERN RED MULTI

## PRODUCT INFORMATION



[www.brickability.co.uk](http://www.brickability.co.uk)

0870 143 3332

Queensgate House, Cookham Road, Bracknell, Berkshire RG12 1RB

Issue Date: January 2025

|           |                             |
|-----------|-----------------------------|
| Packaging | Shrink wrapped & Palletised |
|-----------|-----------------------------|

## TECHNICAL INFORMATION

|                                 |                              |
|---------------------------------|------------------------------|
| Brick Dimensions (L x W x H)    | 215 x 102 x 65mm             |
| Size Tolerances Mean & Range    | T2, R2                       |
| Configuration                   | Perforated                   |
| Voids                           | ≤ 38%                        |
| Mean Compressive Strength       | 35 N/mm <sup>2</sup>         |
| Active Soluble Salts            | S2                           |
| Water Absorption                | ≤10%                         |
| Durability                      | F2                           |
| Gross Dry Density               | 1400 Kg/m <sup>3</sup>       |
| Equivalent Thermal Conductivity | 0,21 W/ mK                   |
| Initial Rate of Absorption      | 0,5 Kg/(m <sup>2</sup> ·min) |